

Vulcan Screening



Overview

Vulcan Screening is created from thermally modified New Zealand plantation timber and engineered with a vertical grain construction for superior weathering characteristics.

The thermal modification process combined with lamination means Vulcan Screening has enhanced stability, reduced resin content, is a beautiful homogenous brown colour, and is naturally durable so does not require any chemical preservatives.

An excellent choice for appearance grade applications such as joinery, pergola, screening, facade fins and ballustrading in-fill.

Wood species:	Thermally Modified Radiata Pine (Pinus Radiata).
Lengths:	Mixed length – Supplied as packets with 1.8m and longer, or fixed lengths at Abodo's option. Fixed length – 3.6, 4.2, 4.8, 5.4m* (subject to availability).
<small>*5.4m lengths are rare. Please inquire on availability. Product supplied as standard in mixed length. Specified fixed length orders may be available but are subject to conditions including minimum quantity, price premium and availability. Please check with Abodo prior to placement of order.</small>	

Sizes:	Stock sizes	Made to order	
	42x18	65x65	
	65x18	88x88	
	88x18	138x138	
	138x18	180x180	
	42x25	180x18	
	65x25	138x25	
	88x25	180x25	
	290x32	42x32	
	238x25	65x32	
	42x42	88x32	
	65x42	138x32	
	88x42	180x32	
	138x42	88x65	
	180x42	138x65	
		180x65	
		65x88	
		138x88	
		180x88	
<small>Note: Supplied as standard with fine band sawn finish four sides. Bandsawn dimension may vary up to +/-2mm. Other sizes are subject to minimum order volumes and lead time.</small>			

Vulcan Screening

Colours:

Colours presented are in Protector – Water Borne and are indicative only.

Colour may change/fade as a part of the natural weathering process.



Product specifications

Name:	Abodo Vulcan Screening.
Quality:	Select Grade /Front face and edges virtually free of any defects but with one edge knot and one small face defect allowed per piece in 20% of boards only. Back side with some defects allowed.
Substrate colour:	Chocolate Brown. (Timber will weather to grey unless a pigmented coating is applied and maintained).
Finish:	Bandsawn faces as standard (smooth dressed subject to confirmation by Abodo). Bandsawn dimension may vary up to +/-2mm (some variation in the visual appearance of the bandsawn finish can be expected).
Durability:	Thermally modified – 230 degrees schedule. No chemical preservatives used. Field tested at SCION, Rotorua. Suitable for uses described in NZS3602:2003 Table 2A 'Requirements for wood-based building to achieve a 15 year durability performance Members exposed to exterior weather conditions and dampness'. Durability Class 1 (EN350-1), Class 2 above ground (AS5604).
Insect attack:	Thermally modified pine is resistant to many wood boring insects but is not always resistant to termites. Preservative treatment is required for termite zones.
Intended use:	Intended for above ground use in residential and light commercial buildings. Not suitable for use in load bearing structural applications or as a primary safety barrier in exterior situations.
Serviceable life:	30 years or more when maintained according to manufacturer's recommendations.
Warranty:	15 years against fungal decay (subject to terms and conditions).
Moisture content:	Approx. 7% MC (+/-2%) at time of dispatch.
Construction:	Laminated with vertical grain orientation.
Glue:	Polyurethane adhesive - VOC, solvent and formaldehyde free. Exterior Type 1 - AS/NZS4364. Approved for Service Class 3 (exposed exterior applications).
Fire:	Group 3 or Group 1S using intumescent coating system.
Expected dimensional change in structure:	Width expansion approx 2%, length expansion approx 0.25%, thickness expansion approx 2.5% (from 7%MC to fibre saturation -variation will occur between boards).

Vulcan Screening

Product specifications

Density:	~420 kg/m3.																					
Hardness:	Low (2.5kN Janka).																					
Thermal properties:	~0.095 W/(mK).																					
pH (indicative):	~ 3.9.																					
Compatibility:	Vulcan has little or no corrosiveness on most metals (separation required to zinc) and can be placed in contact with most building materials. In general cross linking PVA, PU, MUF epoxy glues and RF resins can be used, however a specific adhesive specification may be required considering the low moisture content and unique characteristics of the timber. Please consult with the adhesive supplier and conduct testing prior to commencement of work. Abodo will not be held liable for glue compatibility.																					
Coating:	<p>Vulcan will take most stains, penetrating oils, paints, polyurethanes and varnishes well, though uptake of coating is generally higher than normal.</p> <p>Smooth dressed timber must be thoroughly sanded with 120 grit sand paper prior to application of coating.</p> <p>For exterior applications at least one coat must be applied all sides including back face and ends, and at least two coats to faces and edges exposed to the weather with Protector Water Borne, Sioo:x or other approved coating.</p> <p>Available factory pre-coated (minimum order quantity of 225LM applies).</p> <p>For interior applications film forming or high solids coatings e.g. hard wax oil, acrylic or polyurethane must be used only. Coating can be applied to faces only. Please contact Abodo for further advice on specific application.</p>																					
Quality assurance:	Third party certified to AS/NZS1328.1 and AS/NZS1491.1.																					
Certification:	FSC®- certified mixed, No.: SGS-COC-004944. Declare Certified – Red List Free.																					
Characteristic strength/ stiffness:	<table><tr><th colspan="5">Characteristic strengths (MPa)</th><th colspan="2">Elastic moduli (GPa)</th></tr><tr><th>Gl grade rigidity</th><th>Bending (MOR)</th><th>Tension parallel to grain</th><th>Shear in beam</th><th>Compression parallel to grain</th><th>Short modulus of elasticity parallel to end grain (MOE)</th><th>Short duration modulus for beams</th></tr><tr><td>8</td><td>20.50</td><td>9.60</td><td>-</td><td>38.50</td><td>10.40</td><td>-</td></tr></table>	Characteristic strengths (MPa)					Elastic moduli (GPa)		Gl grade rigidity	Bending (MOR)	Tension parallel to grain	Shear in beam	Compression parallel to grain	Short modulus of elasticity parallel to end grain (MOE)	Short duration modulus for beams	8	20.50	9.60	-	38.50	10.40	-
Characteristic strengths (MPa)					Elastic moduli (GPa)																	
Gl grade rigidity	Bending (MOR)	Tension parallel to grain	Shear in beam	Compression parallel to grain	Short modulus of elasticity parallel to end grain (MOE)	Short duration modulus for beams																
8	20.50	9.60	-	38.50	10.40	-																
Fastening:	<table><tr><th colspan="2">Characteristic lateral load strength</th></tr><tr><td></td><td>Joint Group</td></tr><tr><td>Nail:</td><td>JD4</td></tr><tr><td>Screw:</td><td>JD5</td></tr></table>	Characteristic lateral load strength			Joint Group	Nail:	JD4	Screw:	JD5													
Characteristic lateral load strength																						
	Joint Group																					
Nail:	JD4																					
Screw:	JD5																					

Product handling

- Must be kept clean dry, under cover and out of the weather prior to installation.
- Must be stored horizontally on bearers at least 100mm off the ground.
- Extra care must be taken during installation so as not to damage the factory finish of the boards.
- Wear dust mask, eye protection when cutting timber.
- Non-preserved treated timber may be burnt or mulched. Do not burn preservative treated timber- dispose of off-cuts in lined land fill or an approved furnace.
- Wear gloves when handling to avoid marking the timber surface and to protect against splinters.

Installation

- For exterior appearance applications, high quality stainless steel fixings are recommended. Quality Hot Dip Galvanised may be used in non-appearance applications. Stainless steel 316 (A4) fixings should be used in areas near the sea. Note: Silicone bronze/copper fixings can be subject to oxidation during weathering, resulting in discolouration and weeping around fixing head.
- Fixings at ends of boards must be at least 12mm from edge, and must be pre-drilled before applying fastener.

Vulcan Screening

Installation

- Where possible screening (especially square profiles) should be orientated so that vertical grain pattern is exposed to the prevailing weather. This can be checked by looking at end section.

Vertical grain oriented towards the weather



Weather-exposed face

Weather-exposed face


Note: The above is an overview only. Installers should refer to specific design information on the construction specification for more detail.

- All end grains and notches must be sealed using Abodo's Protector End Seal or equivalent wax sealer, or Sioo:x End Grain Sealer in the case of Sioo:x coated boards. Top exposed end grains of screening must have 15 degree angle applied to shed water. In heavily exposed situations metal caps should be considered to protect end grains at tops of battens.
- Vulcan Screening should generally be installed minimum 100mm above paved surface or 175mm above un-paved surfaces. Base of posts must finish minimum 35mm above paved surface and be sealed to prevent moisture ingress.
- Smooth dressed timber must be thoroughly sanded with 120 grit sand paper prior to application of coating. Bandsawn face timber does not require sanding.
- For exterior applications at least one coat of Protector oil or approved proprietary wood stain must be applied to all sides prior to installation and then a further one or two coats applied once boards are fixed in place according to manufacturer's instructions.
- For interior applications timber may be left uncoated or if coated, film forming or high solids coatings e.g. hard wax oil, acrylic or polyurethane must be used only. Coating can be applied to faces only.


Maintenance

- Wash down every 6-12 months with gentle detergent, warm water and soft brush.
- If possible it is recommended to apply a further coat of oil or stain after approx 12 months of weathering.
- Make a maintenance check every two summers.
- For heavily soiled or mouldy areas use Rejuvenator or similar oxygenating cleaner, active mouldicide and recoat with penetrating oil.
- Re-coat every 2-3 years or as required to maintain colour and integrity of coating. Re-coat period may be longer or shorter depending on climatic conditions and/or positioning of timber to the sun. For Sioo:x coated timber refer to specific maintenance information.


Lightening of the timber:




Vulcan Teak
As delivered



Vulcan Teak
Weathered exterior install



Vulcan Sioo:x
As delivered



Vulcan Sioo:x
Weathered exterior install


We cannot guarantee against wear or color changes to any products which result from weather, sun, wind and/or the natural aging process of the wood.

Vulcan Screening

Maintenance

Surface checking:

- Checking (cracks) may be observed on the face and ends of Vulcan timber. Checks are acceptable to install. Checking may become more apparent as the material weathers naturally in place. Fibre pull at laminated glue lines is also possible. These are not defects and are considered a natural part of this wood product. Maintenance with a coating and thorough sealing of end grains with wax sealer will improve long term weathering characteristics.



Accessories

Abodo Stainless Steel Cladding Screw 4.0mm x 45mm
or 4.5mm x 65mm:



P +64 9 249 0100
E info@abodo.co.nz
W abodo.co.nz